

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A composite material, comprising:
a fiber media, wherein said fiber media comprises at least one
fiber having at least ~~one surface projection~~ two adjacent T-shaped lobes;
at least one intra-fiber void within adjacent T-shaped lobes, where
5 each lobe includes a leg and a cap defining said at least one intra-fiber void
having a diameter larger ~~that~~ than the distance between ~~the~~ ends of the
adjacent caps;
at least one inter-fiber void; and
at least one microcell in contact with said fiber media, wherein
10 said microcell is capable of engaging both the at least one intra-fiber void and
the at least one inter-fiber void due to expansion of the at least one microcell,
where the at least one microcell expands to a diameter larger than the distance
between the adjacent caps.
2. (Original) A composite material as claimed in claim 1, wherein
said fiber media is formed from a polymer.
3. (Original) A composite material as claimed in claim 2, wherein
said polymer is selected from the group consisting of a nylon, a polyester, a
polyolefin and a combination thereof.

4. (Original) A composite material as claimed in claim 2, wherein said polymer is selected from the group consisting of polyester, polypropylene, and nylon 6 with FAV (Formic Acid Viscosity) of at least about 65.

5. (Original) A composite material as claimed in claim 1, wherein said fiber media is formed from a mineral.

6. (Original) A composite material as claimed in claim 5, wherein said mineral is glass.

7. (Original) A composite material as claimed in claim 1, wherein said microcell is an expandable microsphere, whereby said expandable microsphere has an unexpanded form and an expanded form.

8. (Original) A composite material as claimed in claim 7, wherein said unexpanded form is capable of passing into and out of said intra-fiber void and wherein said expanded form is inhibited from passing into and out of said intra-fiber void.

5

9. (Currently Amended) A composite material as claimed in claim 1, wherein said ~~surface projection is a~~ T-shaped lobes are continuously longitudinal lobes.

10. (Currently Amended) A composite material as claimed in claim 1, wherein said fiber has at least ~~two surface projections~~ three T-shaped lobes, and said ~~surface projections~~ T-shaped lobes are continuously longitudinal lobes.

5

11. (Currently Amended) A composite material, comprising:

a fiber media, wherein said fiber media is formed from a polymer and said fiber media comprises at least one fiber having a shape factor of at least about 1.5 and having at least ~~one surface projection~~ two adjacent T-shaped lobes;

at least one intra-fiber void within adjacent T-shaped lobes, where each lobe includes a leg and a cap defining said at least one intra-fiber void having a diameter larger ~~that~~ than the distance between the ends of the adjacent caps;

at least one inter-fiber void; and

at least one expanded microcell in contact with said fiber media, wherein said expanded microcell is capable of engaging both the at least one intra-fiber void and the at least one inter-fiber void due to expansion of the at least one microcell, where the at least one microcell expands to a diameter larger than the distance between the adjacent caps.

12. (Original) A composite material as claimed in claim 11, wherein said shape factor is between about 1.5 and about 6.

13. (Original) A composite material as claimed in claim 11, wherein said shape factor is between about 2 and about 4.

14. (Original) A composite material as claimed in claim 11, wherein said polymer is selected from the group consisting of a nylon, a polyester, a polyolefin and a combination thereof.

15. (Original) A composite material as claimed in claim 11, wherein said polymer is selected from the group consisting of polyester, polypropylene, and nylon 6 with FAV (Formic Acid Viscosity) of at least about 65.

16. (Currently Amended) A composite material as claimed in claim 11, wherein said ~~surface projection is a~~ T-shaped lobes are continuously longitudinal lobes.

17. (Currently Amended) A composite material, comprising:
a fiber media, wherein said fiber media is formed from a polymer selected from the group consisting of polyester, polypropylene, and nylon 6 with FAV (Formic Acid Viscosity) of at least about 65, said fiber media comprises at
5 least one fiber having a shape factor of between about 1.5 and about 6 and having at least two continuously longitudinal T-shaped lobes;
at least one intra-fiber void within adjacent T-shaped lobes, where each lobe includes a leg and a cap defining said at least one intra-fiber void having a diameter larger ~~that~~ than the distance between ~~the~~ ends of the
10 adjacent caps;
at least one inter-fiber void; and
at least one expanded microsphere in contact with said fiber media, wherein said expanded microsphere is capable of engaging both the at least one intra-fiber void and the at least one inter-fiber void due to expansion of
15 the at least one microcell, where the at least one microcell expands to a diameter larger than the distance between the adjacent caps.

18. (Currently Amended) A method for producing a composite material, comprising the steps of:

providing a fiber media, said fiber media comprises at least one fiber having at least ~~one surface projection~~ two T-shaped lobes;

5 forming at least one intra-fiber void and at least one inter-fiber void;

defining said at least one intra-fiber void within adjacent T-shaped lobes each having a leg and a cap, where said at least one intra-fiber void has a

10 diameter larger ~~that~~ than the distance between ~~the~~ ends of the adjacent caps;
and

15 incorporating at least one microcell into said fiber media, wherein
said microcell is capable of engaging both the at least one intra-fiber void and
the at least one inter-fiber void due to expansion of the at least one microcell,
where the at least one microcell expands to a diameter larger than the distance
between the adjacent caps; and

entrapping the at least one microcell within the at least one intra-
fiber void.

19. (Original) A method for producing a composite material as
claimed in claim 18, wherein said microcell is an expandable microcell, and
further comprising the step of applying a triggering energy capable of expanding
said expandable microcell.

20. (Original) A method for producing a composite material as
claimed in claim 18, wherein said fiber media is formed from a polymer.

21. (Original) A method for producing a composite material as
claimed in claim 20, wherein said polymer is selected from the group consisting
of a nylon, a polyester, a polyolefin and a combination thereof.

22. (Original) A method for producing a composite material as
claimed in claim 20, wherein said polymer is selected from the group consisting
of polyester, polypropylene, and nylon 6 with FAV (Formic Acid Viscosity) of at
least about 65.

23. (Original) A method for producing a composite material as
claimed in claim 18, wherein said fiber media is formed from a mineral.

24. (Original) A method for producing a composite material as claimed in claim 23, wherein said mineral is glass.

25. (Currently Amended) A method for producing a composite material, comprising the steps of:

providing a fiber media, wherein said fiber media is formed from a polymer selected from the group consisting of polyester, polypropylene, and
5 nylon 6 with FAV (Formic Acid Viscosity) of at least about 65, said fiber media comprises at least one fiber having a shape factor of between about 2 and about 4, and having at least two continuously longitudinal T-shaped lobes;

forming at least one intra-fiber void and at least one inter-fiber void;

10 defining said at least one intra-fiber void within adjacent T-shaped lobes each having a leg and a cap, where said at least one intra-fiber void has a diameter larger ~~that~~ than the distance between ~~the~~ ends of the adjacent caps;

incorporating at least one expandable microcell into said fiber media, wherein said expandable microcell is capable of engaging said intra-
15 fiber void both the at least one intra-fiber void and the at least one inter-fiber void due to expansion of the at least one microcell, where the at least one microcell expands to a diameter larger than the distance between the adjacent caps;

20 applying a triggering energy to said expandable microcell, wherein said triggering energy is capable of expanding said expandable microcell; and

entrapping the at least one microcell within the at least one intra-fiber void.